

PWF70-YP83EP

Face Material

| weight | thickness | material |
|----------------------------------|----------------------|---------------------------|
| 70 ± 10%g/m ² ISO 536 | 0.09 ± 10%mm ISO 534 | uncoated white matt paper |

Liner

| | | |
|----------------------------------|---------------------|--------------------|
| 80 ± 10%g/m ² ISO 536 | 0.8 ± 10%mm ISO 534 | Yellow kraft paper |
|----------------------------------|---------------------|--------------------|

Adhesive

This is an adhesive with high initial viscosity and high end viscosity. It has excellent performance on many packaging materials. It can be used for information labels of food, books and periodicals, wine, beverages, electrical appliances and cultural goods.

Peel adhesion

| | | |
|--|--|--|
| Initial adhesion 10N/25mm FTM 9 st.st | 20 minutes Peel adhesion value on steel at 180° 16N/25mm or tear off FTM 1 st.st | 20 minutes Peel adhesion value on steel at 90° 9N/25mm or tear off FTM 2 st.st |
|--|--|--|

Temperature

| | |
|------------------------|--|
| Min. Appl. Temp. 10 °C | Service Temp. -10°C+90°C (after 24hrs) |
|------------------------|--|

Applications

This product has good adhesion properties and is widely used in price tags, computer printed labels and matte labels.

The above suggestion, application, and elaboration are not intended as the guarantee of Jinya. All sales of Jinya products shall be tested by customer in the final environment to confirm compliance with the requirements of the use of environment.

Printing Methods

The surface material has excellent ink absorption and is suitable for a variety of printing methods, including laser and inkjet printing. Matte paper with a rough surface, suitable for printing and printing of simple graphics. Used in office, logistics and other industries.

Shelf life

12 months, applicable only to the material delivered by Jinya which has not undergone further processing, under the following **STORAGE CONDITIONS**:

- This material must be stored at a temperature of 23 ± 2°C and 50 ± 5% of Relative Humidity.
- Storage area must be dry and clean.
- Keep the material in the original packaging when not used in order to protect it from dust and contamination.
- Do not expose to direct sunlight or heat sources.