

FWMPP75-W58AD

Removable Label

Face Material

weight	thickness	material
55g / m ² ± 10% ISO536	0.75mm ± 10% ISO534	Matte milky white polypropylene film with special coating on the surface

Liner

58g / m ² ± 10% ISO536	0.055mm ± 10% ISO534	white glassine paper with super calender treatment
-----------------------------------	----------------------	----------------------------------------------------

Adhesive

AD is a removable adhesive with high resilience of appropriate initial viscosity, excellent wetting ability on the surface of the object to be pasted, and good final removability and viscosity. It can be repeatedly torn and pasted on many non-paper stickers without leaving residual glue. Wide range of normal operating temperature .

Peel adhesion

initial adhesion 6 N/25mm or tear off FTM9	20 mins Peel adhesion value on steel at 180 angle 3 N/25mm or tear off FTM1	20 mins Peel adhesion value on steel at 90 angle 2N/25mm or tear off FTM2
-----------------------------------------------	--------------------------------------------------------------------------------------	---------------------------------------------------------------------------------

Temperature

Min. Appl. Temp. 5 °C	Service Temp. -20°C +60°C (24H after labeling)
-----------------------	------------------------------------------------

Applications

The product has excellent tensile strength, tear strength, stable physical and chemical properties, opaque, and has certain shading and barrier properties. It has the removable performance of repeated pasting on many pasted products, and is widely used in special fields such as sanitary napkin sealing paste, kitchen utensils and household appliances. Due to the different surface properties of the objects to be pasted, it is recommended to carry out label pasting test on the objects to be pasted before putting them into use. Stable size and chemical corrosion resistance, suitable for making various durability labels.

The above suggestion, application, and elaboration are not intended as the guarantee of Jinya. All sales of Jinya products shall be tested by customer in the final environment to confirm compliance with the requirements of the use of environment.

Printing Methods

Sub-white polypropylene film with paper visual effect, with a layer of coating on the surface, can be used for flexographic printing, letterpress printing, screen printing, heat transfer printing and other printing methods, and has good performance on ink. Product labels with important properties such as water resistance, oil resistance and chemicals have excellent covering performance on the dark bottle body. Sharp cutting tools shall be used in die cutting, and label overflow caused by too tight winding tension shall be avoided at the same time.

Shelf life

12 months, applicable only to the material delivered by Jinya which has not undergone further processing,

under the following **STORAGE CONDITIONS:**

- This material must be stored at a temperature of 23 ± 2°C and 50 ± 5% of Relative Humidity.
- Storage area must be dry and clean.
- Keep the material in the original packaging when not used in order to protect it from dust and contamination.
- Do not expose to direct sunlight or heat sources.